

Cryotreatment

by Jack Cahn, Chief Technologist, DCI, jack@deepcryogenics.com

Mechanisms Behind Deep Cryogenic Treatment in Ground Engagement Tools

Deep cryogenic treatment (DCT) has become an important enhancement process for ground engaging tools (GETs). These components operate in some of the harshest service environments where abrasive wear, repeated impact loading, and cyclic fatigue combine to cause premature failure. Unlike conventional heat treatment alone, DCT modifies the internal microstructure of alloys at temperatures approaching -300°F (-184°C), creating improvements that directly address the dominant failure modes seen in mining GET applications.

Primary Failure Modes in Mining Ground-Engaging Tools

In mining applications, GETs fail primarily through two mechanisms: progressive fatigue cracking and catastrophic impact fracture. A shovel tooth repeatedly striking blasted rock experiences extremely high cyclic compressive and tensile stresses. Even when the surface appears intact, microscopic fatigue cracks initiate at carbide interfaces, inclusions, or residual tensile stress regions. Over thousands of loading cycles these cracks propagate until the tooth fractures. DCT improves resistance to this process by altering residual stress distributions, refining carbide precipitation and stabilizing the alloy matrix structure. (Figure 1)

DCT Mechanisms in High Chrome White Iron

For high chrome white iron GETs, the mechanism is especially important because these alloys derive their wear resistance from large chromium carbides embedded within a martensitic matrix. Under heavy impact loading, retained austenite (left over from the casting process) can transform unpredictably, generating localized stresses that accelerate crack formation. During DCT, much of this retained austenite transforms into fine martensite, increasing matrix




Figure 1. Deep cryogenic treatment of shovel teeth. Credit: J. Cahn

uniformity and dimensional stability. This reduces carbide pullout and suppresses micro-crack nucleation at carbide boundaries—both common initiation points for fatigue failure in white iron mining components.

DCT Benefits in 13% Manganese Alloy Steel

In 13% manganese alloy steels (commonly used where high-impact toughness

is required) the benefits of DCT are somewhat different. Hadfield manganese steel is valued because it work-hardens during service while retaining a tough austenitic core. Bucket teeth and crusher components made from manganese steel survive severe impact because the alloy absorbs energy without brittle fracture. DCT enhances this behavior by refining dislocation structures and promoting more uniform strain hardening

under impact conditions. Research on high-manganese TWIP/TRIP steels shows that cryogenic processing and related surface treatments can increase compressive residual stresses and improve cyclic performance.

Role of Residual Stress in Fatigue Resistance

The importance of compressive residual stress for mining GETs cannot be overstated. Fatigue cracks grow most readily under tensile stress. DCT-induced compressive stresses counteract service-induced tensile loads, making it mechanically more difficult for cracks to open and propagate. This results in fewer tooth breakages and reduced risk of losing fragments into crushers. (Figure 2)

Impact Resistance and Structural Durability

Mining shovel teeth frequently encounter shock loads from large boulders. Conventional hardening processes often increase hardness at the expense of toughness, making the component more brittle. DCT differs because it refines the microstructure without producing the coarse brittle phases associated with over-hardening. The fine carbide distribution generated during cryogenic soaking helps disperse impact energy more evenly through the alloy matrix. This reduces localized stress concentrations that normally trigger brittle fracture.

Difference Between DCT in Cutting Tools and Mining GETs

The performance improvements seen in heavy equipment GETs differ significantly from those observed in carbon steel cutting tools used in edge-retention applications. In knives, dies, and machining tools, DCT primarily improves edge sharpness retention and abrasive wear resistance. The mechanism centers on converting retained austenite to martensite and precipitating extremely fine eta carbides that strengthen the cutting edge. The primary benefit is reduced edge rounding and slower abrasive wear during sliding contact.

Mining GETs operate under entirely different loading conditions. Bucket teeth are not precision cutting tools; they are large structural wear components exposed to




Figure 2. Residual Stress. Credit: J. Cahn




Figure 3. DCT wear life improvement. Credit: J. Cahn

high-impact gouging abrasion and repeated shock loading. Consequently, the value of DCT in GETs is less about maintaining a sharp edge and more about extending structural integrity under cyclic stress. The dominant improvements are enhanced fatigue resistance, reduced crack propagation, improved impact toughness and more stable work-hardening behavior. While abrasive wear resistance still improves, the greatest economic benefit often comes from preventing catastrophic tooth breakage and increasing service reliability in severe mining environments. (Figure 3)

Conclusion

Ultimately, DCT functions as a microstructural optimization process that enhances both wear and mechanical durability. For high chrome white iron and 13% manganese alloy GETs, the treatment creates a more stable, refined, and fatigue-resistant structure capable of surviving the extreme combination of abrasion and impact encountered in mining operations. By addressing crack initiation and propagation at the microscopic level, DCT provides measurable improvements in operational life, maintenance reduction, and equipment reliability. 🧊