Cryotreatment

by Jack Cahn, Chief Technologist, DCI, jack@deepcryogenics.com

The Physics of Cryogenic Treatment

Previous "Cryotreatment" columns for ***Cold Facts*** have explored material selection, cryo chamber design, and the science behind cryogenic treatment. But from a physics perspective: what are the thermal challenges of deep cryogenic treatment and how does payload size influence process success?

Temperature Change

Cryogenic treatment is a controlled thermal process used to improve the wear resistance, dimensional stability, and service life of metals and engineered components. Unlike conventional heat treatment, cryogenic treatment subjects materials to temperatures approaching -320° F using liquid nitrogen-promoting beneficial microstructural transformations. Although the objective appears to be simply cooling an item, removing heat from a large object in a controlled manner is considerably more difficult than adding it. This challenge is governed by thermodynamics, heat transfer, thermal inertia, and advanced process control.

Thermodynamics and Thermal Inertia

The first law of thermodynamics states that energy cannot be created or destroyed, only transferred or converted. During cryogenic treatment, thermal energy is removed from the workpiece until the target temperature is reached. The second law of thermodynamics explains why cooling is inherently more difficult than heating. Heat naturally flows from higher to lower temperatures, increasing entropy. Heating is relatively straightforward because energy is actively supplied through electrical resistance heaters or combustion. However, cooling depends on extracting heat and transporting it away — relying on temperature gradients, heat transfer, and the cooling medium's (LN_2) ability to absorb energy.

Figure 1. Chamber vs material temp - 10,000 lb payload on the way -294 °F. *Credit: J. Cahn*

A key factor is thermal inertia—an object's resistance to temperature change which depends on mass, density, and specific heat capacity. Large steel components retain substantial internal energy after their surfaces have cooled, creating temperature gradients between the cooler exterior and warmer core. (Figure 1) If cooling occurs too quickly, the surface contracts while the interior remains warmer, generating thermal stresses that can distort or crack the component.

Newton's law of cooling provides the mathematical framework for this behavior. The rate of heat transfer is proportional to the temperature difference between an object and its surroundings. When a warm component enters a cryogenic chamber, the large temperature difference allows rapid heat removal. As the component cools, this difference decreases and the cooling rate naturally slows. Therefore, maintaining a controlled, near-linear cooling profile requires continuous adjustment rather than simply exposing the load to a fixed cold environment.

Chamber Design, Challenges, and Solutions

Modern cryogenic systems achieve this through precisely metered injections of liquid nitrogen into insulated chambers. Programmable logic controllers (PLCs) regulate nitrogen flow according to predetermined time-temperature profiles. Multiple sensors monitor chamber and product temperatures, while proportional-integral-derivative (PID) algorithms continuously adjust nitrogen flow to minimize deviations from the desired cooling curve.

The challenge increases significantly with large, dense industrial payloads. (Figure 2) Their high thermal inertia requires

the removal of substantial quantities of heat before the target temperature is reached. Meanwhile, the chamber is surrounded by a warmer environment, creating a continuous inward heat flow. Although high performance insulation greatly reduces this transfer, heat still enters through structural supports, door seals, pipe penetrations, and geometric discontinuities such as corners and joints. These localized heat leaks create non-uniform temperature distributions that must be corrected by the control system. (Figure 3)

The chamber itself also becomes part of the thermal system. As its internal surfaces cool, they absorb heat conducted through the insulation from the surrounding environment, effectively acting as a thermal wick. This heat load varies with ambient temperature, humidity, insulation condition, and chamber geometry. Consequently, liquid nitrogen must remove heat from both the payload and chamber structure.

These unavoidable thermal losses interrupt the cooling process. Each injection of liquid nitrogen must first offset incoming environmental heat before further reducing the payload temperature. The resulting cooling curve reflects the combined effects of payload thermal inertia, chamber heat capacity, insulation performance, and external heat infiltration. Without active feedback control, temperature overshoot or undershoot would compromise process repeatability and the metallurgical transformations responsible for improved wear resistance.

Therefore, cryogenic treatment is far more than exposing components to extreme cold. It is a sophisticated application of thermodynamics requiring precise control of energy transfer, thermal gradients, and cooling rates. By combining the first and second laws of thermodynamics, Newton's law of cooling, advanced PLC-PID control, and carefully engineered chamber design, cryogenic processors achieve the thermal profiles needed to enhance wear resistance while avoiding thermal damage. The process demonstrates a fundamental engineering principle: removing heat with precision is often significantly more challenging than supplying it.

Figure 2. Slow cooling a 14,000 crusher liner payload. *Credit: J. Cahn*



Figure 3. Infrared readings of thermal losses. *Credit: J. Cahn*

Success depends not simply on reaching ultralow temperatures, but on managing the complex movement of thermal energy throughout the treatment cycle. By applying sound engineering principles and precise process control, cryogenic treatment transforms extreme cold into measurable improvements in material performance, reliability, and longevity.

CRYOGENIC REFERENCES

Explore CSA's List of Cryogenic References

CSA provides a list of cryogenic references, including conference proceedings, journals, periodicals, books, websites, and more. The references are available online and as a PDF. Click through now to discover something new and be sure to contact editor@cryogenicsociety.org to recommend additional resources.

www.cryogenicsociety.org/cryogenic-references